

sterkteklasse	Minimale karakteristieke cilindersterkte $f_{ck:cil}$ N/mm ²	Minimale karakteristieke kubussterkte $f_{ck:kub}$ N/mm ²
C8/10	8	10
C12/15	12	15
C16/20	16	20
C20/25	20	25
C25/30	25	30
C30/37	30	37
C35/45	35	45
C40/50	40	50
C45/55	45	55
C50/60	50	60
C55/67	55	67
C60/75	60	75
C70/85	70	85
C80/95	80	95
C90/105	90	105
C100/115	100	115